## IN THE CLAIMS:

- 1. (original) A process for preparing catalyst systems of the Ziegler-Natta type, which comprises the following steps:
  - A) bringing an inorganic metal oxide into contact with a tetravalent titanium compound and
  - B) bringing the intermediate obtained from step A) into contact with a magnesium compound MgR<sup>1</sup><sub>n</sub>X<sup>1</sup><sub>2-n</sub>, where X<sup>1</sup> are each, independently of one another, fluorine, chlorine, bromine, iodine, hydrogen, NRX2, ORX, SRX, SO3RX or OC(O)RX, and R<sup>1</sup> and R<sup>X</sup> are each, independently of one another, a linear, branched or cyclic C<sub>1</sub>-C<sub>20</sub>-alkyl, a C<sub>2</sub>-C<sub>10</sub>-alkenyl, an alkylaryl having 1-10 carbon atoms in the alkyl 6-20 part and, carbon in the atoms aryl part or a  $C_6$ - $C_{18}$ -aryl and n is 1 or 2,
  - bringing the intermediate obtained from step B) into contact with a halogenating reagent of the formula R<sup>Y</sup><sub>s</sub>-E-Y<sub>4-s</sub> where R<sup>Y</sup> are each, independently of one another, hydrogen, a linear, branched or cyclic C<sub>1</sub>-C<sub>20</sub>-alkyl, a C<sub>2</sub>-C<sub>10</sub>-alkenyl, an alkylaryl having 1-10 carbon atoms in the alkyl part and 6-20 carbon atoms in the aryl part or a C<sub>6</sub>-C<sub>18</sub>-aryl, E is carbon or silicon, Y is fluorine, chlorine, bromine or iodine and s is 0, 1, 2 or 3 when E is carbon and s is 1, 2 or 3 when E is silicon.

1

- 2. (original) A process for preparing catalyst systems as claimed in claim 1, wherein a magnesium compound MgR<sup>1</sup><sub>2</sub> is used in step B).
- (currently amended) A process for preparing catalyst systems as claimed in <u>claim 1</u> or 2, wherein the halogenating reagent used in step C) is chloroform.
- 4. (currently amended) A process for preparing catalyst systems as claimed in <u>claim 1</u> any of claims 1 to 3, wherein the inorganic metal oxide used in step A) is a silica gel.
- 5. (currently amended) A process for preparing catalyst systems as claimed in <u>claim 1</u> any of claims 1 to 4, wherein the tetravalent titanium compound used in step A) is titanium tetrachloride.
- 6. (currently amended) A process for preparing catalyst systems as claimed in <u>claim 1</u> any of claims 1 to 5, which comprises the following steps:
  - A) bringing an inorganic metal oxide into contact with a tetravalent titanium compound
  - B) bringing the intermediate obtained from step A) into contact with a magnesium compound MgR<sup>1</sup><sub>n</sub>X<sup>1</sup><sub>2-n</sub>, where X<sup>1</sup> are each, independently of one another, fluorine, chlorine, bromine, iodine, hydrogen, NR<sup>X</sup><sub>2</sub>, OR<sup>X</sup>, SR<sup>X</sup>, SO<sub>3</sub>R<sup>X</sup> or OC(O)R<sup>X</sup>, and R<sup>1</sup> and R<sup>X</sup> are each, independently of one another, a linear, branched or cyclic

 $C_1$ - $C_{20}$ -alkyl, a  $C_2$ - $C_{10}$ -alkenyl, an alkylaryl having 1-10 carbon atoms in the alkyl part and 6-20 carbon atoms in the aryl part or a  $C_6$ - $C_{18}$ -aryl and n is 1 or 2.

- c) bringing the intermediate obtained from step B) into contact with a halogenating reagent of the formula R<sup>Y</sup><sub>s</sub>-E-Y<sub>4-s</sub>, where R<sup>Y</sup> are each, independently of one another, hydrogen, a linear, branched or cyclic C<sub>1</sub>-C<sub>20</sub>-alkyl, a C<sub>2</sub>-C<sub>10</sub>-alkenyl, an alkylaryl having 1-10 carbon atoms in the alkyl part and 6-20 carbon atoms in the aryl part or a C<sub>6</sub>-C<sub>18</sub>-aryl, E is carbon or silicon, Y is fluorine, chlorine, bromine or iodine and s is 0, 1, 2 or 3 when E is carbon and s is 1, 2 or 3 when E is silicon, and
- D) optionally bringing the intermediate obtained from step C) into contact with a donor compound.
- 7. (original) A process for preparing catalyst systems as claimed in claim 6, wherein the donor compound used in step D) contains at least one nitrogen atom.
- 8. (currently amended) A catalyst system of the Ziegler-Natta type which can be prepared by a process as claimed in claim 1 any of claims 1 to 7.
- 9. (original) A prepolymerized catalyst system comprising a catalyst system as claimed in claim 7 and linear C<sub>2</sub>-C<sub>10</sub>-1-alkenes polymerized onto it in a mass ratio of from 1:0.1 to 1:200.

3

- 10. (currently amended) A process for the polymerization or copolymerization of olefins at from 20 to 150°C and pressures of from 1 to 100 bar in the presence of at least one catalyst system as claimed in claim 8 or 9 and, if appropriate, an aluminum compound as cocatalyst.
- 11. (original) A process for the polymerization or copolymerization of olefins as claimed in claim 10, wherein a trialkylaluminum compound whose alkyl groups each have from 1 to 15 carbon atoms is used as aluminum compound.
- 12. (currently amended) A process for the polymerization or copolymerization of olefins as claimed in claim 10 or 11, wherein ethylene or a mixture of ethylene and C<sub>3</sub>-C<sub>8</sub>-α-monoolefins is (co)polymerized.
- 13. (currently amended) The use of a catalyst system as claimed in claim 8 or 9 for the polymerization or copolymerization of olefins.